

IColor™ Presto! 1-Step Metallic Transfer Paper Instructions For Cardboard, Paper and Wood Applications

AVAILABLE IN LETTER SIZE

Temperature	Time	Paper Setting	Pressure
265°F / 130°C	90 Seconds	IColor™ 500/600 - Media Type: Labels / Media Weight: UH1 IColor™ 650 - Media Type: User Type 2 / / Media Weight: Med Heavy 105 IColor™ 560 – Paper Type: Thick to 105g IColor™ 540/550 - Paper Type: Coated Glossy IColor™ 800 - Paper Type: Thick to 163g	High

IColor™ Presto! 1 Step Metallic Transfer Paper for Cardboard, Paper and Wood is an easy to use, all-in-one paper for use with a variety of monochrome, white toner, CMYK Laser/LED printers and copiers. Print in black and press in gold or silver onto cardboard, paper or wood. No cutting or weeding necessary! IColor™ Presto! 1 Step Metallic Transfer Paper for Cardboard, Paper and Wood does not require coated substrates.

Designed to work with the IColor™ series of specialty printers, the IColor™ Presto! 1 Step Metallic Transfer Paper for Cardboard, Paper and Wood will also work with many popular color and monochrome laser printers – please check with your printer manufacturer to be certain. Works best with vector graphics and fonts. Add distress to the image for a vintage look.

RECOMMENDED COLOR SETTINGS:

- IColor™ 650 / 600 / 560 / 550 / 540 / 500:
 - 100% Black. Set cartridges standard CMYK configuration with black cartridge. Print in monochrome.
- CMYK Printers:
 - 100% Black. Print in monochrome or greyscale.
- IColor™ 800 / Other white toner printers:
 - 300% Composite Black (100% Cyan, 100% Magenta, 100% Yellow)
- Monochrome Printers:
 - 100% Black with full density

INSTRUCTIONS FOR BEST RESULTS:

1. Place the Presto! transfer sheet into the appropriate tray of the IColor™ printer.
 - ▲ The colored side is the print side.
 - IColor™ 650 / 600 / 500 / Most OKI Printers: Print side face up in Multipurpose Tray
 - IColor™ 560 / 550 / 540 / 800: Print side face down in the Multipurpose Tray
 - ▲ You may need to stack a few sheets in the tray at once so the printer pulls the media cleanly (except the IColor™ 560).

2. Printer Settings:

- ⚠ Specific print modes for this media are available when using the IColor™ ProRIP or ProRIP Essentials software.
 - Listed as ‘Uninet Presto! Hard Surface Wood & Paper’
 - Be sure you are printing in the CMYK queue.
- IColor™ 500 / 600 / Most OKI Printers: Set media weight to ‘Ultra Heavy 1’ and media type to ‘Labels’
- IColor™ 650: Set media weight to ‘Ultra Heavy 105 – 120g’ and media type to ‘User Type 2’
- IColor™ 550 / 540 users: Set paper type to ‘Coated Glossy’
- IColor™ 560: Set Paper type to ‘Thick to 105g’
- IColor™ 800: Set paper type to ‘Thick to 163g’
- Page size should be ‘Letter’.
- ⚠ Remember to set the job to **mirror print**, ensuring the correct orientation when transferred to the textile.

3. Print the image.

4. Set the temperature of the heat press to 265°F / 130°C and preheat.

Swing away or clam shell press:

Substrate	Time	Temp	Press Pressure	Peeling
Cardboard, Paper or Wood	90 Sec	265°F / 130°C	9 (High)	Warm

5. Place a piece of kraft paper on the lower plate of the heat press.

- Align the printed image to the substrate and lay flat on the press, with the IColor™ Presto! Paper on top (image facing the substrate).
- You can tape the hard surface paper to the lower kraft paper for additional stability.

6. Carefully cover the transfer with a silicon pad (.5mm - 1mm is suggested for best results).

- Ensure the transfer does not shift positions during this step

7. Press at 265°F / 130°C for 90 seconds with high pressure.

8. Open press and carefully remove the substrate.

- Place on a steady surface upside down (transfer closest to the surface) and place a heavy object on top for 1 minute to prevent warping.
- This will ensure the transfer uniformly adheres to the substrate.

9. Remove the heavy object and peel the transfer paper from the substrate in one smooth motion.

TECH TIPS

There are many variables that could produce different results. Specific steps may need to be altered based on:

- **Type and brand of Heat Press:** The temperature and duration varies slightly based on the heat press being used. All instructions are based on using a Hotronix Fusion press. Clam shell and swing away presses may also yield different results.

- **Type of substrate:** Some substrates may require more or less press time, depending on the material and the image being pressed. Recommended settings can vary greatly, especially with substrates of varying thickness. The use of a digital thermometer placed between the substrate and the transfer will result in more consistent results.

- **Type of image:** Full coverage graphics may require a longer press time than vector images or text.

- **Toner Coverage:** Toner coverage should not be less than 50% otherwise there will be issues with transferring.

The use of a silicon pad or foam pad is necessary when using the Hard Surface Paper.

- All instructions are based on a .5mm silicon pad, which is available from UNINET. Thicker pads (greater than 1mm) will require longer press times and higher temperatures.
- In these cases, the use of a thermometer can help to establish the best settings. It is suggested to use the foam pad that comes with the media for glass / crystal applications.

The use of kraft paper below and above your project is highly recommended. This way, you can easily remove your substrates from the press.

If you are using tape to secure your image to the substrate, make sure the tape is not covering any part of the transfer, as that will lead to inconsistent results.

For all applications (especially wood, where the polymer from the hard surface paper is transferred over), it is suggested that the size of your transfer paper is larger than your substrate for an easier pull and to avoid differences in the sheen.

If a particular instruction is not working for you, try varying pressure, press time, higher or lower temp, longer or shorter dwell time.

Optimal Humidity Level: 45% - 65%

- Regulated with A/C, a humidifier or de-humidifier, depending on current atmospheric conditions.

Optimal Temperature Range: 50°F / 10°C - 75°F / 24°C

Use of this media outside of these recommend parameters may lead to poor results.

To see video instructions for IColor™ 1-Step Presto!! Metallic Transfer Paper for Cardboard, Paper and Wood visit www.icolorprint.com/video

ALSO AVAILABLE:

- IColor™ Premium 2 Step Transfer Paper for light and dark colored garments
- IColor™ Select and Select Ultra Bright 2 Step Transfer Paper for light and dark colored garments
- IColor™ Standard 2 Step Transfer Paper for light and dark colored garments
- IColor™ Glitter Adhesive 2 Step Transfer Paper (for use with IColor™ Standard 2 Step Transfer Paper)
- IColor™ Light 1-Step Transfer Paper for light colored garments
- IColor™ Presto 2 Step Transfer Paper for textiles and hard surfaces
- IColor™ Premium 2 Step Temporary Tattoo, Easy Tattoo and Easy Tattoo Pro Transfer Paper
- IColor™ Premium and Wood and Leather Hard Surface 1-Step Transfer Paper
- IColor™ AquaClear 1-Step Decal Transfer Paper for candles and other substrates not resistant to heat
- IColor™ Label / Sticker Paper (Clear and White) in Letter and Tabloid size
- IColor™ Window Cling Media (Clear and White) in Banner and cut sheet options
- IColor™ Banner Paper
- IColor™ Magnetic Media in Letter and Tabloid size

...and more! Contact your dealer for more information.

IColor™ Transfer Paper Comparison Charts

ICOLOR TEXTILE TRANSFER PAPER

ATTRIBUTE	PREMIUM	STANDARD	STANDARD B PRO	SELECT UB	SELECT	PRESTO	LIGHT
PROCESS	2 Step	2 Step	2 Step	2 Step	2 Step	2 Step	1 Step
DURABILITY (# of Washes @ 104 °F/40 °C)	Up to 100	50+	50+	50+	50+	50+	15+
DARK TEXTILES (BRILLIANCE)	BEST	BETTER	BETTER	BEST	GOOD	BETTER	FAIR
DELICATE TEXTILES	BEST	GOOD	GOOD	GOOD	GOOD	GOOD	NOT RECOMMENDED
STRETCHABILITY	BETTER	GOOD	BEST	BEST	BEST	GOOD	GOOD
FINISH	MATTE	SEMI GLOSS	SEMI GLOSS	MATTE	MATTE	SEMI GLOSS	SATIN
TRANSFER 'A' SHEET CHARACTERISTIC	OPAQUE	TRANSPARENT	TRANSPARENT	TRANSPARENT	TRANSPARENT	OPAQUE	OPAQUE
PRESS TEMPERATURE (°F/°C)	260°F / 120°C	310°F / 154°C	310°F / 154°C	320°F / 160°C	310°F / 154°C	285°F / 140°C	390°F / 200°C
PRESS TIME	30 + 30 secs	120 + 30 secs	120 + 30 secs	135 + 25 secs	120 + 25 secs	120 + 30 secs	15 secs
SOFT HAND	BEST	GOOD	GOOD	GOOD	GOOD	GOOD	BETTER
EASE OF USE / RELIABILITY	BETTER	BETTER	BETTER	GOOD	BEST	BETTER	GOOD
COST	\$\$\$	\$	\$	\$	\$	\$	\$

ICOLOR HARD SURFACE TRANSFER PAPER

ATTRIBUTE	PREMIUM	WOOD/LEATHER	PRESTO! HARD SURFACE	PRESTO! PAPER/WOOD	AQUACLEAR	2 STEP TATTOO	1 STEP TATTOO
PROCESS	1 Step	1 Step	1 Step	1 Step	1 Step	2 Step	1 Step
DURABILITY (RESISTANT TO SCRATCHING/CHIPPING)	BEST	BEST	BEST	BEST	GOOD	BETTER	GOOD
COLOR BRILLIANCE	BETTER	BETTER	BEST	BEST	BETTER	BETTER	BETTER
METALLIC FINISH	NO	NO	YES	YES	NO	NO	NO
PRESS TEMPERATURE (°F/°C)	300°F / 150°C *	300°F / 150°C *	320°F / 160°C *	265°F / 130°C *	N/A	265°F / 130°C	N/A
PRESS TIME	60 SECS *	60 SECS *	180 SECS *	90 SECS *	N/A	40 SECS	N/A
ACRYLIC	YES	YES	YES	NO	YES	YES	YES
METAL	YES	NO	YES	NO	YES	YES	YES
CERAMIC	YES	NO	YES	NO	YES	YES	YES
TILE	YES	NO	YES	NO	YES	YES	YES
GLASS	YES	YES	YES	NO	YES	YES	YES
CRYSTAL	YES	YES	YES	NO	YES	YES	YES
PAPER/WOOD/CARDBOARD	YES	YES	YES	YES	NO	YES	NO
LEATHER	YES	YES	NO	NO	NO	YES	NO
CANDLES	NO	NO	NO	NO	YES	YES	YES
FLESH	NO	NO	NO	NO	NO	YES	NO
COST	\$	\$	\$\$	\$\$	\$\$	\$\$\$	\$\$

* Temperature and press time varies based on substrate

UPDATED JAN 2025

ICOLOR PAPERS WORK WITH ALL WHITE TONER PRINTERS!

February 2025 Revision - A newer version of this manual may be available at www.icolorprint.com/support

(Or scan this QR Code)

